



TEST REPORT

DATE: 06-13-2019

Page 1 of 1

TEST NUMBER: 0257861

CLIENT	Palziv North America
---------------	----------------------

TEST METHOD CONDUCTED	ASTM D3575 Compression Resistance Strength
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Eco Cork Foam (ECF) Underlayment
CONSTRUCTION	Cushion

GENERAL PRINCIPLE

The samples were prepared and tested to measure the compression resistance strength at varied deflections as listed in the results section.

TEST RESULTS

TEST DESCRIPTION	METHOD	RESULTS
Compression Strength @ 10%	ASTM D3575	608.4 lbs/foot ²
Compression Strength @ 25%	ASTM D3575	1,350.0 lbs/foot ²
Compression Strength @ 50%	ASTM D3575	3,355.2 lbs/foot ²
Compression Strength @ 60%	ASTM D3575	5,014.8 lbs/foot ²
Compression Strength @ 70%	ASTM D3575	8,276.4 lbs/foot ²
Compression Strength @ 80%	ASTM D3575	17,632.8 lbs/foot ²

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.